

# Gantrail® 1400 MP

Multi-Purpose, Deep Pour Precision Grout  
Standard/High Flow

www.gantrail.com



Gantrail® 1400 MP is an expansive, nonshrink, low exotherm epoxy grout system for the precision grouting of crane runway systems. This versatile, multi-purpose product is formulated for single, large volume placements and may be used as thin as 1/2 inch (13 mm) in depth. Gantrail 1400 MP is a three component, 100% solids, solvent-free system formulated to provide high strength and superior creep resistance combined with the highest effective bearing area. Gantrail 1400 MP exhibits positive expansion when tested in accordance with ASTM C 827.

## ADVANTAGES

- Low exotherm with early strength development
- Long working time
- Solvent-free clean up
- Adjustable flow for various conditions
- Expansive, nonshrink per ASTM C 827
- Superior creep resistance
- Chemically resistant
- 95% Effective Bearing Area (EBA) is typically achieved following proper grouting procedures
- Excellent adhesion to steel

## USES

- Precision alignment of crane runway systems under dynamic load conditions.

## PACKAGING & YIELD

Gantrail 1400 MP is a three component system consisting of partially filled containers of resin, hardener and polyethylene lined bags of aggregate. Gantrail 1400 MP - Standard Flow includes five bags of aggregate for a unit yield of approximately 2.0 cubic feet (56.6 litres) of hardened material. When maximum flow is required, Gantrail 1400 MP - High Flow is available with four bags of aggregate for a unit yield of approximately 1.75 cubic feet (49.6 litres) of hardened material.

## SHELF LIFE

Two years in original unopened packaging when stored in dry conditions; high relative humidity will reduce shelf life.

### \*TYPICAL PROPERTIES AT 70°F (21°C)

	Gantrail 1400 MP (Standard)		Gantrail 1400 MP (High Flow)		
Clearances	1 to 18 inches (25 - 457 mm)		1/2 to 9 inches (13 - 220 mm)		
Height Change, ASTM C 827, at 90°F (32°C)	Positive Expansion		Positive Expansion		
Effective Bearing Area	95%		95%		
Creep, ASTM C 1181, 1 year 400 psi (2.8 MPa) 140°F (60°C)	3.7 x 10 <sup>-3</sup> in/in (mm/mm)		4.3 x 10 <sup>-3</sup> in/in (mm/mm)		
Tensile Strength, ASTM C 307	2100 psi (14.5 MPa)		2000 psi (13.8 MPa)		
Flexural Strength, ASTM C 580	3800 psi (26.2 MPa)		4000 psi (27.6 MPa)		
Coefficient of Expansion, ASTM C 531	17 x 10 <sup>-6</sup> in/in/°F (30 x 10 <sup>-6</sup> mm/mm/°C)		18 x 10 <sup>-6</sup> in/in/°F (32 x 10 <sup>-6</sup> mm/mm/°C)		
Bond to Concrete, ASTM C 882	Concrete Failure		Concrete Failure		
Working Time at 70°F (21°C)	90 minutes		60 minutes		
Compressive Strength ASTM C 579 B*	Standard Compressive Strength psi (MPa)	Standard Compressive Modulus psi (MPa)	High Flow Compressive Strength psi (MPa)	High Flow Compressive Modulus psi (MPa)	
	1 Day	11000 (75.9)	1.5 x 10 <sup>6</sup> (10.4 x 10 <sup>3</sup> )	9000 (62.1)	1.4 x 10 <sup>6</sup> (9.7 x 10 <sup>3</sup> )
	7 Days	14000 (96.6)	2.0 x 10 <sup>6</sup> (13.8 x 10 <sup>3</sup> )	13000 (89.7)	1.9 x 10 <sup>6</sup> (13.1 x 10 <sup>3</sup> )
	Post cured at 140°F (60°C)	17000 (117.2)	2.2 x 10 <sup>6</sup> (15.2 x 10 <sup>3</sup> )	16000 (110.3)	2.0 x 10 <sup>6</sup> (13.8 x 10 <sup>3</sup> )

\*Materials tested per ASTM C 579 B. Rate of loading 0.25 inches per minute. The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result. Test methods are modified where applicable.

# Gantrail® 1400 MP

## Multi-Purpose, Deep Pour Precision Grout Standard/High Flow

### PLACEMENT GUIDELINES

- SURFACE PREPARATION:** All surfaces to be in contact with Gantrail 1400 MP shall be free of oil, grease, laitance and other contaminants. Concrete must be clean, sound, dry and roughened to ensure a good bond. An SSPC-SP6 commercial finish on all metal surfaces will optimize bond development to steel.
- FORMWORK:** Formwork shall be constructed of rigid non-absorbent materials, securely anchored, liquid-tight and strong enough to resist forces developed during grout placement. The clearance between formwork and baseplate shall be sufficient to allow for a headbox. The clearance for remaining sides shall be 1 to 2 inches (25 - 50 mm). Areas where bond is not desired must be treated with paste wax or polyethylene. Isolation joints may be necessary depending on pour dimensions.
- MIXING:** For optimum performance, all components should be conditioned to between 70°F and 80°F (21°C and 27°C) prior to use. Pour all Component B (hardener) into pail containing Component A (resin). Mix thoroughly by hand with a paddle or with a slow speed drill and paddle mixer to avoid air entrapment. Pour mixed liquids into mortar mixer (stationary barrel with moving blades). While mixing, slowly add Component C (aggregate) and mix only until aggregate is completely wet. Add Component C (aggregate) immediately after mixing Component A (resin) and Component B (hardener). Working time is approximately 90 minutes (60 minutes High Flow) when temperatures are at 70°F (21°C).
- METHODS OF PLACEMENT:** Gantrail 1400 MP may be poured into place. All grout shall be placed from one side to the other, maintaining contact with the bottom of the baseplate at all times. When possible, use of a headbox is highly recommended. For clearances greater than eighteen inches (457 mm), contact Gantry Railing Ltd. at +44 (0) 1452 300688.
- POST-PLACEMENT PROCEDURES:** Final finishing should ensure material is flush with bottom edge of soleplate. Finishing of exposed surfaces is aided by using a solvent wiped trowel just before material becomes unworkable. In-service operation may begin immediately after minimum required grout strength and modulus have been achieved.
- CLEAN UP:** All tools and equipment may be cleaned with a water and strong detergent solution before material hardens. Sand may be used as an abrasive. A suitable solvent is required for clean up of material after hardening.

**NOTE: PRIOR TO APPLICATION, READ ALL PRODUCT PACKAGING THOROUGHLY.**

### CAUTION

- Flowability and strength gain are adversely affected by lower temperatures.
- For placement temperatures below 55°F (13°C) or above 90°F (32°C), call Gantry Railing Ltd. at +44 (0) 1452 300688.
- To obtain bond, concrete shall be visibly free of surface moisture.
- Do not add solvents to increase flowability.
- For continuous operating temperatures exceeding 180°F (82°C), contact Gantry Railing Ltd.
- Construction practices dictate concrete foundation should achieve its design strength before grouting.

Irritant, toxic, strong sensitizer. Contains epoxy resin and amine. This product may cause skin irritation. Do not inhale vapors. Provide adequate ventilation. Protect against contact with skin and eyes. Wear rubber gloves, long sleeve shirt, goggles with side shields. In case of contact with eyes, flush repeatedly with water and contact a physician. Areas of skin contact should be promptly washed with soap and water. Do not take internally. Keep product out of reach of children. **PRIOR TO USE, REFER TO MATERIAL SAFETY DATA SHEET.**

For more information on the complete product line or for technical assistance, please contact Gantrail.

WARRANTY STATEMENT FOR ALL GANTRY RAILING LTD. PRODUCTS MANUFACTURED BY FIVE STAR PRODUCTS, INC.: "FIVE STAR PRODUCTS INC. (FSP) PRODUCTS ARE MANUFACTURED TO BE FREE OF MANUFACTURING DEFECTS AND TO MEET FSP'S CURRENT PUBLISHED PHYSICAL PROPERTIES WHEN APPLIED IN ACCORDANCE WITH FSP'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM AND FSP STANDARDS. HOWEVER, SHOULD THERE BE DEFECTS OF MANUFACTURING OF ANY KIND, THE SOLE RIGHT OF THE USER WILL BE TO RETURN ALL MATERIALS ALLEGED TO BE DEFECTIVE, FREIGHT PREPAID TO FSP, FOR REPLACEMENT. THERE ARE NO OTHER WARRANTIES BY FSP OF ANY NATURE WHATSOEVER, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THIS PRODUCT. FSP SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT, INCLUDING PUNITIVE, ACTUAL, REMOTE, OR CONSEQUENTIAL DAMAGES, RESULTING FROM ANY CLAIMS OF BREACH OF CONTRACT, BREACH OF ANY WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FROM ANY OTHER CAUSE WHATSOEVER. FSP SHALL ALSO NOT BE RESPONSIBLE FOR USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT HELD BY OTHERS."



## A world of crane rail expertise.

[www.gantrail.com](http://www.gantrail.com)



**Gantry Railing Ltd**  
Sudmeadow Road  
Hempstead  
Gloucester GL2 5HG  
ENGLAND

Tel: +44 (0) 1452 300688  
Fax: +44 (0) 1452 300198  
E-mail: [info@gantrail.com](mailto:info@gantrail.com)

**Gantrail (Middle East) Ltd**  
P O Box 61428  
Jebel Ali Free Zone  
Dubai  
United Arab Emirates

Tel: +971 4 8812 935  
Fax: +971 4 8812 936  
E-mail: [gme@gantrail.com](mailto:gme@gantrail.com)



Gantrail 1400 MP/ET/5/11